



HARDENER FOR POLYX®-OIL EXPRESS

Special hardening additive for Polyx®-Oil Express – reduces drying times!



6632
Clear



PRODUCT DESCRIPTION

Special clear polyisocyanate hardening additive for Osmo Polyx®-Oil Express to reduce drying time.

RECOMMENDED USE

Osmo Hardener for Polyx®-Oil Express acts as an additive for Osmo Polyx®-Oil Express for accelerated drying.

INGREDIENTS

Aliphatic polyisocyanate, methoxy propyl acetate. Detailed declaration of ingredients available upon request.

TECHNICAL DATA

Specific weight: 1.15 g/cm³
Viscosity: 36s (4 mm, DIN 53211)
Odour: faint/mild, odourless after drying
Flashpoint: >45 °C acc. DIN 53213

STORAGE

1 year and longer if can is kept dry and closed tightly. Leftover product mixture cannot be stored and reused.

SURFACE PREPARATION

The surface preparation before use of Osmo Polyx®-Oil Express are not influenced by the application of the hardener additive. These are valid without any restrictions. For this purpose, please observe the product information for Osmo Polyx®-Oil Express. The finished surface is influenced by several factors, including the condition of the wood. Therefore, a trial application is always required, especially for unfamiliar surfaces.

METHODS OF APPLICATION

Add Osmo Hardener for Polyx®-Oil Express completely to the can of Polyx®-Oil Express (2.5 litre) and stir so that both components are mixed well. Further processing to be carried out corresponds to that of Polyx®-Oil Express.

Note: Pot time is reduced down to 90 minutes by adding the Hardener. Please do not mix together more material than you can process with certainty within 60 minutes. If you do not use the entire can of Polyx®-Oil Express, add 6% Hardener – mix in a separate container!

CLEANING OF TOOLS

With Osmo Brush Cleaner (benzene-free).

DRYING TIME

Approx. 1-2 hours (normal climatic conditions, 23 °C/ 50 % rel. humidity). Lower temperatures and/or higher air humidity can increase the drying time. Ventilate well while drying.

COVERAGE

The product coverage of Polyx®-Oil Express is not changed by adding hardener.

NOTE

Pot time is reduced down to 90 minutes by adding the Hardener. Please do not mix together more material than you can process with certainty within 60 minutes.

CAUTION

Flammable liquid and vapour. Harmful if inhaled. Contains isocyanates. May produce an allergic reaction. May cause respiratory irritation.



CAUTION

Keep out of reach of children. Read label before use. Keep away from heat/open flames. No smoking. Do not breathe mist/vapours/spray. Wear protective gloves. If medical advice is needed, have product container or label at hand. Use only outdoors or in a well-ventilated area. IF ON SKIN: Wash with plenty of water and soap. IF INHALED: Remove person to fresh air and keep comfortable for breathing. Product contains: Hexamethylene 1,6-diisocyanato homopolymer.

Warning



DISPOSAL

Dispose of leftover product and completely emptied packaging according to local official guidelines (waste code number 08 05 01). Only completely emptied cans can be recycled.

COLOUR TONE

6632 Clear

SIZE

0.15 L

The above mentioned information is provided to the best of our knowledge however without any liability.

Version 02/17